

DATE 9/2/52

SH. 1 OF 1

COMPILED BY
[Signature]

TMC SPECIFICATION NO. S-126

TITLE: WOOD PRESERVATIVE, CREOSOTE

JOB 111

APPROVED *[Signature]*

CREOSOTE TREATMENT

THE WOOD SHALL BE TREATED WITH AN EIGHT POUND CHARGE OF
CREOSOTE PER CUBIC FOOT OF WOOD IN ACCORDANCE WITH
AWPA SPECIFICATIONS P1-51, C-1 AND C-2.