

DATE 4-15-63

SHEET 1 OF 1

# TMC SPECIFICATION NO. S -756

J.R. HEITZER  
TMC-I  
COMPILED

J.R. 6/25/63  
C.M.P.  
CHECKED

TITLE: GRAY SYNTHETIC ENAMEL

YFH  
APPROVED

6.26.63

## COLOR:

Munsel Gray Number 4.5, Variable Gloss dependent upon Plastic surface. Approximately 40 - 50.

## MATERIAL:

No. 23-1902 Superior Gray Synthetic Epoxy Enamel  
No. 2-185 Synthetic Thinner

## SOURCE:

The Chemical Coatings Corp., Rocky Hill, Conn.

## SURFACE PREPARATION:

Clean surface with No. 2-185 Thinner.

## APPLICATION:

Apply one uniform coat.

Bake 20 Minutes at 225°F. (107°C.)